

IN THE CLAIMS:

1. (Currently amended) A method of indicating the presence of mechanical impact on a material, comprising the steps of  
providing the material having a surface;  
preparing an indicator paint having an impact-sensitive component that produces a visible change when subjected to a mechanical impact, wherein the indicator paint comprises a mixture of a first reactant and a second reactant separated by a barrier that is rupturable so that the first reactant and the second reactant mix and produce the visible change when the indicator paint is subjected to the impact;  
applying the indicator paint to the surface of the material;  
placing the material having the indicator paint thereon into circumstances where it may be subject to the mechanical impact; and thereafter  
inspecting the material having the indicator paint thereon for the presence of the visible change.
2. (Original) The method of claim 1, wherein the step of providing includes the step of  
providing the material as a low-ductility material having a tensile elongation to failure of less than about 2 percent.
3. (Original) The method of claim 1, wherein the step of providing the material includes the step of  
providing a composite material having a tensile elongation to failure of less than about 2 percent.
4. (Original) The method of claim 1, wherein the step of providing the material includes the step of  
providing a polymer-matrix composite material having a tensile elongation to failure of less than about 2 percent.

5. (Original) The method of claim 1, wherein the step of providing the material includes the step of  
providing a ceramic material having a tensile elongation to failure of less than about 2 percent.

6. (Currently amended) The method of claim 1, wherein the step of preparing the indicator paint includes the step of  
preparing the indicator paint having the impact-sensitive component that changes color when subjected to the mechanical ~~impact~~; impact.

7. (Cancel)

8. (Currently amended) The method of claim 1, wherein the step of preparing the indicator paint includes the step of  
preparing the indicator paint comprising  
an encapsulated first reactant, and  
a the second reactant,  
wherein the first reactant and the second reactant react together to produce the visible change upon the impact.

9. (Original) The method of claim 1, wherein the step of preparing the indicator paint includes the step of  
preparing the indicator paint that does not emit light when subjected to the mechanical impact.

10. (Original) The method of claim 1, wherein the step of placing includes the step of  
not instrumenting the material having the paint thereon with light-detection instrumentation.

11. (Original) The method of claim 1, wherein the step of inspecting includes the step of

inspecting the material having the indicator paint thereon by an unaided eye.

12. (Original) The method of claim 1, including an additional step, after the step of inspecting, of  
determining a design limit for the composite material responsive to an observability of impact indications.

13. (Currently amended) The method of claim 1, including an additional step, after the step of inspecting, of  
determining a first design limit for the composite material in the event that it has the indicator paint applied thereto, and a second design limit for the composite material in the event that it has no indicator paint applied ~~thereto.~~ thereto.

14. (Original) A method of indicating the presence of mechanical impact on a composite material, comprising the steps of  
providing the composite material having a surface, wherein the composite material has a tensile elongation to failure of less than about 2 percent;  
preparing an indicator paint having an impact-sensitive component that changes color when subjected to a mechanical impact, wherein the indicator paint comprises  
a first reactant, and  
a second reactant,  
wherein the first reactant and the second reactant are separated by a barrier that is ruptured when the indicator paint is subjected to the mechanical impact;  
applying the indicator paint to the surface of the composite material;  
placing the composite material having the indicator paint thereon into circumstances where it may be subject to the mechanical impact; and thereafter  
inspecting the composite material having the indicator paint thereon for the presence of a color change.

15. (Original) The method of claim 14, wherein the step of preparing the indicator paint includes the step of  
preparing the indicator paint that does not emit light when subjected to the

mechanical impact.

16. (Original) The method of claim 14, wherein the step of placing includes the step of  
not instrumenting the composite material having the paint thereon with light-detection instrumentation.

17. (Original) The method of claim 14, wherein the step of inspecting includes the step of  
inspecting the composite material having the indicator paint thereon by an unaided eye.

18. (Original) The method of claim 14, including an additional step, after the step of inspecting, of  
determining a design limit for the composite material responsive to an observability of impact indications.

19. (Currently amended) The method of claim 14, including an additional step, after the step of inspecting, of  
determining a first design limit for the composite material in the event that it has the indicator paint applied thereto, and a second design limit for the composite material in the event that it has no indicator paint applied ~~thereto.~~ thereto.

20. (Currently amended) An article comprising:  
a substrate having a surface; and  
a paint applied to the surface of the article, wherein the paint comprises  
a plurality of microcapsules, and wherein each microcapsules comprises a first reactant, and  
a matrix comprising a paint binder and a second reactant, wherein the plurality of microcapsules is mixed with and embedded in the matrix,  
and wherein ~~where~~ the first reactant and the second reactant produce a color in the paint when mixed.

21. (Original) A method for establishing a design standard for a low-ductility material, comprising the steps of:

setting a first design standard for the low-ductility material having an indicator paint applied thereto, wherein the indicator paint has an impact-sensitive component that produces a visible change when subjected to a mechanical impact; and

setting a second design standard for the low-ductility material which does not have the indicator paint applied thereto.

22. (Original) The method of claim 21, wherein the step of setting the first design standard includes the step of

setting the first design standard with a unity damage-tolerance factor, and wherein the step of setting the second design standard includes the step of

setting the second design standard with a damage-tolerance factor greater than unity.

23. (Original) The method of claim 21, wherein the step of setting the first design standard includes the step of

setting the first design standard with a first damage-tolerance factor, and wherein the step of setting the second design standard includes the step of

setting the second design standard with a second damage-tolerance factor that is greater than the first damage tolerance factor.

24. (New) The method of claim 14, wherein the step of preparing includes the step of

preparing the indicator paint as a mixture of the first reactant and the second reactant.